

Technical Data Sheet

ROHRflex-PA 12F+

ROHRflex corrugated plastic tubings


Multilayer corrugated plastic tubing especially for outdoor applications

Temperature: -50°C ... +120°C ^ +150°C
-58°F ... +248°F ^ +302°F

Material: PA 12 plastics

Characteristics:

- High alternate bending strength under extreme climatic conditions
- Oil and benzine resistant
- Widely resistant to acid and solvents
- Free of silicone, cadmium, halogen
- Highly self-extinguishing
- Flame retardant
- Excellent UV-resistance



Applications:

- Railway industry especially for outside applications and tunnels




Characteristics	Unit	Value	Test
Mechanical characteristics			
Resistance to compression	N	320	EN 61386-23
Resistance to bending		flexible	EN 61386-23
Resistance to impact (-45C)	J	2	EN 61386-23
Resistance to impact (-15C)	J	6	EN 61386-23
Resistance to reversed bending		5,000	EN 61386-23
Average reversed bending stress		>2,000,000	WN-1003
Flame characteristics			
Free of halogen and phosphor		yes	DIN 53474
Flame class		V2	UL 94
Resistance to flame propagation		non flame propagating	EN 61386-23
Flammability of rail vehicle materials		flame retardant	JRMA
Railway EN 45545-2			
Fire hazard level R22 and R23		HL3	EN 45545-2
Oxygen index	%	>32	ISO 4589-2
Smoke density	DS max.	>150	EN ISO 5659-2
Toxicity	CIT	<0.75	NF X 70-100-1/-2
Specific characteristics			
Resistance to fuels, mineral oil, fat alkalises, glycols, acids, bases		excellent	
Weather performance			
UV-resistance	Std.	1,000	ASTM G155, Cycle 1
System test			
Pull-out resistance with FLEXAquick	N	250	EN 61386-23
Ingress protection			
Assembled with FLEXAquick		IP 68/69K	IEC 60529

Technical Data Sheet

ROHRflex-PA 12F+

ROHRflex corrugated plastic tubings

Multilayer corrugated plastic tubing especially for outdoor applications



Part Number	Color	Trade Size mm in	Profile	ID mm in	OD mm in	BR Stat. mm in	BR Dyn. mm in	Weight kg/m lb/ft	Std Pack m ft
1249.202.006	Black	10.0 1/4	Fine	6.6 0.26	10.0 0.39	13 0.51	35 1.38	0.020 0.01	50 164
1249.202.010	Black	13.0 5/16	Fine	9.9 0.39	13.0 0.51	15 0.59	45 1.77	0.025 0.02	50 164
1249.202.012	Black	15.8 3/8	Fine	12.3 0.48	15.9 0.63	25 0.98	55 2.17	0.040 0.03	50 164
1249.202.016	Black	21.2 1/2	Fine	16.7 0.66	21.5 0.85	35 1.38	75 2.95	0.070 0.05	50 164
1249.202.023	Black	28.5 3/4	Coarse	21.6 0.85	28.7 1.13	55 2.17	100 3.94	0.105 0.07	50 164
1249.202.029	Black	34.5 1	Coarse	27.7 1.09	34.7 1.37	65 2.56	120 4.72	0.125 0.08	25 82
1249.202.036	Black	42.5 1 1/4	Coarse	35.7 1.41	42.5 1.67	90 3.54	150 5.91	0.150 0.10	25 82
1249.202.049	Black	54.5 1 1/2	Coarse	46.7 1.84	54.5 2.15	100 3.94	190 7.48	0.250 0.17	25 82

Recommendations for any areas of applications, products, or product combinations are issued to the best of FLEXA's knowledge and experience. The user is requested to check applicability of FLEXA products to specific applications and purposes prior to the use of the particular products. All documentation, illustrations, and charts published are subject to copyright and must not be copied, changed, used, or modified. Technical drawings, certificates, authorizations, and results by the FLEXA lab will be provided upon request. FLEXA will not be held liable for typographical or other errors and incorrect drawings. Technical modifications are subject to change without prior notice.